DEUTSCH COLOR

HANSA SPACHTEL





Water based, acrylicic-silicon grout, ready for use, suitable for interior surface rendering.

CHARACTERISTICS

- · Does not create cracks
- · Does not shrink
- Strong bonding
- White colour
- · Final smooth finish
- · Easy application and grinding

RECOMMENDATIONS FOR USE

It is used for wall polishing on all the interior spaces where we want to create a smooth surface of inner walls, rooms, kitchen, toilette surfaces, etc.

SURFACE PREPARATION

The surfaces should be completely dry, clean and free from dust or elements that hinder the adhesion of the product.

PRODUCT PREPARATION

The product is ready for application. It is recommended to homogenize the product, mixing it with an electric mixer before use.

TECHNICAL DATA

Basis:	Acrylic copolymer
Density EN ISO 2811- 1:	1,75±0,02 gr/ml
Dry residue EN ISO 3251:	70%
Mixing ratio:	Ready for use
Colour:	White
Tensile adhesion strength in concrete:	≥ 0,8 N/mm ²
Consumption:	1Kg/m ²
Drying time between two coatings:	2 – 4 hours
Drying time for grinding:	24 hours
Drying time for painting:	72 hours
Compressive strength:	≥ 400 N

DEUTSCH COLOR

APPLICATION OF PRODUCT

Application of the product Hansa Spachtel is done with a metal notched trowel. Spread the product on the surface to be treated and bring it to the required thickness. The application thickness of a coating shall not exceed 3 mm. The product must be applied in two coatings. Clean the spatula and other working tools with water immediately after application.

STORAGE

24 months if stored in a dry place, away from heat sources, at a temperature between +5°C and +30°C. Protect it from frost.

CONSUMPTION

2.5- 5 Kg/m² depends on grain size

PACKAGING

2,2 Kg plastic buckets

HEALTH AND SAFETY INFORMATION

Keep out of reach of children. In case of contact with the eyes or swallowing, please seek medical advise immediately and show the contents of the container. Do not dispose the product into drains.

NOTE

- In fresh concrete surfaces the product should be applied at least after 30-40 days. It is recommended to avoid the application of the product at temperatures below 5° C.





