# DEUTSCH COLOR

## **MÖRTEL M15**



Working time:

Setting time:

Maximum thickness:

### **DESCRIPTION**

Basic filling material for brick or block walls for indoor and outdoor environments

### **CHARACTERISTICS**

Powder material, with cement, lime, stone sand of selected granulometry, synthetic resins and special additives.

- It is characterized by excellent workability.
- · High mechanical resistance
- Free of vertical slip
- · Adhesion abilities in walls and ceilings

### **RECOMMENDATIONS FOR USE**

It is used as a basic mortar for all types of supports, such as: brick or block walls, etc. The product is applied through a piece of machinery or hand. During the application of the product, the support and environment temperature should be from +5°C up to +35°C.

### **SURFACE PREPARATION**

The support where the material will be applied must be dry, clean, uniform, absorbent, and stable. There should be no external residues, such as: oils, varnishes, petroleum, etc. On the support in which the material will be applied, there should be no external phenomenons such as fluorescence.

# Form: Colour: Combustibility Incombustible: Incombustible Water demand: Consistence: Application temperature: Powder Form: Grey Incombustible Incombustible 5.5 – Lt / 25 Kg Thixotropic 45°C up to +35°C Pot life: 3 - 4 Hours

30 min

400 min

3 cm

**TECHNICAL DATA** 

Deutschcolor sh.a Autostrada Tiranë - Durrës, km 19, Durrës - Albania, Tel: +355 57 59 4000, info@deutschcolor.de, www.deutschcolor.de

# DEUTSCH COLOR

### PRODUCT PREPARATION

Mix 25 Kg of powder MORTEL M15 with 5.5-6 liters of water through an electric agitator or manually until acquiring an appropriate mixture for the required application. You can also work with a pump.

### **APPLICATION**

The product is applied manually, with a trowel or mechanically with a pump. When the product is applied with a pump you should pay attention to the consistency of processing. Do not add other materials, except for Latex. In the case of long pauses, the agitator should be left empty and be cleaned. Fresh mortar should be processed within 2 hours. Protect the bricks and mortar (especially, during work interruption) from rain. In cases of high temperatures, it is better to slightly water the mortar before it gets dried, so as not to lose its water.

### REINFORCEMENT WITH LATEX

To improve the adhesiveness, resistance to water, plasticity, flexibility, mechanical strength, etc., the mortar can be reinforced with Latex additive. The mixing ratio is 1: 5 in water (see technical sheet Latex).

### STORAGE

12 months after manufacture date if the product is stored in its original and unopened packaging, in environments protected by moisture and frost.

### **CONSUMPTION**

Approximately 15 Kg/m<sup>2</sup> for cm thickness.

### **PACKAGING**

25 Kg paper bags

### **HEALTH AND SAFETY INFORMATION**

Keep out of reach of children. In case of contact with the eyes or swallowing, please seek medical advise immediately and show the contents of the container. Do not dispose the product into drains.





